

Product Literature

Characteristics

These low-protein, powder-free gloves eliminate air-borne particles of latex protein associated with powdered surgical gloves. Ultra-low modulus is designed for greater comfort, less hand fatigue during long surgical procedures.



PRODUCT DETAILS

SIZE	ITEM NO.	PACKAGING	DESCRIPTION
5.5	133550	50 pairs/box, 4 boxes/case	
6	133600	50 pairs/box, 4 boxes/case	
6.5	133650	50 pairs/box, 4 boxes/case	Gloves, Surgical, Latex, Sterile, Powder-Free, Textured
7	133700	50 pairs/box, 4 boxes/case	
7.5	133750	50 pairs/box, 4 boxes/case	
8	133800	50 pairs/box, 4 boxes/case	
8.5	133850	50 pairs/box, 4 boxes/case	
9	133900	50 pairs/box, 4 boxes/case	

Features

- Textured
- Low Modulus
- Low Protein

Benefits

- Improved Wet/Dry Grip
- · Softer More Comfortable Fit
- Reduced Chances of Latex Allergic Reactions

Product Solutions You Trust



Specification Sheet

₩ DermAssist



Sterile Pairs

LATEX SURGICAL GLOVES POWDER-FREE

Product Attributes

- Textured
- Low Modulus
- Low Protein

Benefits

- Improved Wet/Dry Grip
- · Soft, More Comfortable Fit
- Reduced Chances of Latex Allergic Reactions

DermAssist® is manufactured in compliance with multiple international standards, including the following:

Designation	Standard	
ASTM D3577	Standard Specification for Rubber Surgical Gloves	
ASTM D5151	Standard Test Method for Detection of Holes in Medical Gloves	
ASTM F1671	Standard Test Method for Resistance of Materials Used in Protective Clothing to Penetration by Blood-Borne Pathogens	
ASTM D5712	Standard Test Method for Analysis of Aqueous Extractable Protein in Natural Rubber	

Average Length	Average Palm Thickness	Average Finger Thickness
11.5 in ◆ 290 mm	8.3 mil ◆ 0.21 mm	8.7 mil ◆ 0.22 mm

Tensile Strength & Elongation	Before Aging	After Accelerated Aging
Tensile Strength (Mpa)	28	24
ASTM Requirement Min. (Mpa)	18	14
Elongation (%)	850	820
ASTM Requirement Min. (%)	650	500





