

# Product Literature

## **Characteristics**

These low-protein, powder-free gloves eliminate air-borne particles of latex protein associated with powdered surgical gloves. Ultra-low modulus is designed for greater comfort, less hand fatigue during long surgical procedures.



#### **PRODUCT DETAILS**

SIZE	ITEM NO.	PACKAGING	DESCRIPTION	
5.5	133550	50 pairs/box, 4 boxes/case		
6	133600	50 pairs/box, 4 boxes/case	Gloves, Surgical, Latex, Sterile,	
6.5	133650	50 pairs/box, 4 boxes/case		
7	133700	50 pairs/box, 4 boxes/case		
7.5	133750	50 pairs/box, 4 boxes/case	Powder-Free, Textured	
8	133800	50 pairs/box, 4 boxes/case		
8.5	133850	50 pairs/box, 4 boxes/case		
9	133900	50 pairs/box, 4 boxes/case		

### **Features**

- Textured
- Low Modulus
- Low Protein

#### **Benefits**

- Improved Wet/Dry Grip
- · Softer More Comfortable Fit
- Reduced Chances of Latex Allergic Reactions

Product Solutions You Trust



# Specification Sheet



POWDER-FREE

LATEX

SURGICAL GLOVES



DermAssist® is manufactured in compliance with multiple international standards, including the following:

Designation	Standard	
ASTM D3577	Standard Specification for Rubber Surgical Gloves	
ASTM D5151	Standard Test Method for Detection of Holes in Medical Gloves	
ASTM F1671	Standard Test Method for Resistance of Materials Used in Protective Clothing to Penetration by Blood-Borne Pathogens	
ASTM D5712	Standard Test Method for Analysis of Aqueous Extractable Protein in Natural Rubber	

Average Length	Average Palm Thickness	Average Finger Thickness
11.6 in ◆ 295 mm	7.5 mil <b>→</b> 0.19 mm	8.0 mil <b>→</b> 0.20 mm

Tensile Strength & Elongation	Before Aging	After Accelerated Aging
Tensile Strength (Mpa)	30	24.5
ASTM Requirement Min. (Mpa)	24	18
Elongation (%)	1290	1150
ASTM Requirement Min. (%)	750	560



Innovative Healthcare Corporation is certified to ISO 13485:2003 QMS for medical devices.



Product Solutions You Trust
1-800-272-1533

272**-1**533 <sub>1338-070915</sub>